


**AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Original) Crystal oriented ceramics composed of a polycrystalline substance of an isotropic perovskite compound represented by the general formula:



(wherein,  $0 \leq x \leq 0.2$ ,  $0 \leq y \leq 1$ ,  $0 \leq z \leq 0.4$ ,  $0 \leq w \leq 0.2$ ,  $x + z + w > 0$ ), and a specific crystal plane of each crystal grain that composes said polycrystalline substance is oriented.

2. (Currently Amended) Crystal oriented ceramics according to claim 1 wherein, the specific crystal plane is degree of orientation of the pseudo-cubic {100} plane and its degree of orientation as determined according to the Lotgering method is 30% or more.

3. (Original) Crystal oriented ceramics according to claim 1 wherein, the piezoelectric  $d_{31}$  constant at room temperature is 1.1 times or more that of a non-oriented sintered compact having the same composition.

4. (Original) Crystal oriented ceramics according to claim 1 wherein, the electromechanical coupling coefficient  $k_p$  at room temperature is 1.1 times or more that of a non-oriented sintered compact having the same composition.

5. (Original) Crystal oriented ceramics according to claim 1 wherein, the piezoelectric  $g_{31}$  constant at room temperature is 1.1 times or more that of a non-oriented sintered compact having the same composition.

6. (Original) Crystal oriented ceramics according to claim 1 wherein, the rate of improvement resulting from orientation in displacement generated under electric field driving

conditions having a constant amplitude of an electric field strength of 100 V/mm or more at a predetermined temperature equal to or below the Curie temperature is 1.1 times.

7. (Original) Crystal oriented ceramics according to claim 1 wherein, there is a temperature range where the amount of fluctuation of displacement under electric field driving conditions having a constant amplitude of an electric field strength of 100 V/mm or more over an arbitrary temperature range of 100°C or more equal to or lower than the Curie temperature is within  $\pm 20\%$ .

8. (Original) Crystal oriented ceramics according to claim 1 wherein, there is a temperature range where the amount of fluctuation of  $E_{33\text{large}}$  as measured according to formula A1 under electric field driving conditions having a constant amplitude of an electric field strength of 100 V/mm over an arbitrary temperature range of 100°C or more equal to or lower than the Curie temperature is within  $\pm 15\%$ ; wherein, the amount of polarization is measured from a polarization-electric field hysteresis loop in the case of driving by applying a high voltage, and  $E_{33\text{large}}$  is the dielectric constant in a strong electric field based on this (dynamic dielectric constant), and is defined by equation A1:

$$E_{33\text{large}} = P_{\text{max}} / (EF_{\text{max}} \times \epsilon_0) = (Q_{\text{max}} / A) / (V / L \times \epsilon_0) \quad \text{A1}$$

(wherein, Here,  $P_{\text{max}}$  represents the maximum charge density ( $\text{C}/\text{m}^2$ ),  $EF_{\text{max}}$  represents the maximum electric field strength ( $\text{V}/\text{m}$ ),  $Q_{\text{max}}$  represents the maximum charge (C), A represents the electrode surface area ( $\text{m}^2$ ),  $\epsilon_0$  represents the dielectric constant in a vacuum ( $\text{F}/\text{m}$ ), L represents the original length prior to applying a voltage (m), and V represents the applied voltage (V)).

9. (Original) ) Crystal oriented ceramics according to claim 1 wherein, there is a temperature range where the amount of fluctuation of the value defined by  $D_{33\text{large}} / (E_{33\text{large}})^{1/2}$

under electric field driving conditions having a constant amplitude over an arbitrary temperature range of 100°C or more equal to or lower than the Curie temperature is within  $\pm 10\%$ ; wherein,  $D_{33\text{large}}$  is the displacement generated in a direction parallel to the direction in which voltage is applied in the case of applying a high voltage, and is defined by equation A2:

$$D_{33\text{large}} = S_{\text{max}}/EF_{\text{max}} = (\Delta L/L)/(V/L) \quad \text{A2}$$

(wherein,  $S_{\text{max}}$  represents the maximum strain,  $\Delta L$  represents the displacement induced by the electric field (m),  $L$  represents the original length prior to applying a voltage (m), and  $V$  represents the applied voltage (V)).

10. (Currently Amended) Crystal oriented ceramics according to claim 1 wherein, there is a temperature range where the amount of fluctuation of the value defined by  $D_{33\text{large}}/E_{33\text{large}}$  under electric field driving conditions having a constant amplitude over an arbitrary temperature range of 100°C or more equal to or lower than the Curie temperature is within  $\pm 9\% \pm 8\%$ .

11. (Original) Crystal oriented ceramics according to claim 1 wherein, there is a temperature range where the amount of fluctuation of displacement generated under constant energy driving conditions over an arbitrary temperature range of 100°C or more equal to or lower than the Curie Temperature is within  $\pm 10\%$ .

12. (Currently Amended) Crystal oriented ceramics according to claim 1 wherein, there is a temperature range where the amount of fluctuation of displacement generated under constant charge driving conditions over an arbitrary temperature range of 100°C or more equal to or lower than the Curie temperature is within  $\pm 9\% \pm 8\%$ .

13. (Currently Amended) Crystal oriented ceramics according to claim 1 wherein, ~~the a~~ crystal system of said crystal grain is a tetragonal system over an arbitrary temperature range of 100°C or more equal to or lower than the Curie temperature.

14. (Currently Amended) A production method of crystal oriented ceramics comprising:

a mixing step in which a ~~first~~ an anisotropic shaped powder of plate-like crystal material, for which ~~the~~ a crystal growth plane has lattice coherency with a specific crystal plane ~~of the~~ isotropic perovskite compound according to claim 1, is mixed with a ~~first~~ reaction raw material that can reacts therewith said ~~first~~ anisotropic shaped powder and at least forms the to form an isotropic perovskite compound of claim 1;

a molding step in which the mixture obtained in the mixing step is molded so that the specific first anisotropic shaped powder crystal planes are ~~is~~ oriented; and,

a heat treatment step in which the molded product obtained in the molding step is heated to cause a reaction between the ~~first~~ anisotropic shaped powder and the ~~first~~ reaction raw material to form a crystal oriented ceramic material as in claim 1.

15. (Currently Amended) A crystal oriented ceramics production method according to claim 14 wherein, the ~~first~~ anisotropic shaped powder is a plate-like powder having the pseudo-cubic {100} plane for its growth plane and is represented by the following general formula:



(wherein, x, y, z and w are  $0 \leq x \leq 1$ ,  $0 \leq y \leq 1$ ,  $0 \leq z \leq 1$  and  $0 \leq w \leq 1$ , respectively).

16. (Original) A piezoelectric element comprised of a piezoelectric material composed of crystal oriented ceramics according to claim 1.

17. (Original) A dielectric element comprised of a dielectric material composed of crystal oriented ceramics according to claim 1.

18-19. (Cancelled).